

# ProFast Topcoat 703-AS

## Description and application

ProFast Topcoat 703-AS is an autocatalytic, solvent free, anti-slip topcoating based on polyurea combinations. ProFast Topcoat 703-AS is suitable for outdoor applications.

ProFast Topcoat 703-AS has quick drying properties and is ideal for the treatment of walkways, balconies, terraces and galleries.

## Article number and packaging

16223-5	5,17 kg set
16223-10	10,35 kg set

## Properties

- Quick curing
- Zero shrinkage
- UV-proof
- Excellent preservation of colour and gloss
- Completely water resistant
- For out- and indoor applications
- Very low dirt absorption
- Good chemical resistance
- Up to 3 times more wear and scratch resistant than traditional flooring systems
- Resistant against plasticizers

## Thermal

Load	Dry heat
Permanent	+80 °C
Brief (a maximum of 7 days)	+100 °C
Brief (a maximum of 12 hours)	+120 °C

Short-term wet heat up to a maximum of +80 °C and only occasionally, for instance when steam-cleaning. Simultaneous chemical and mechanical loads are not permitted.

## Properties liquid product

Colour	Available in RAL colours, see colour overview. <i>Other colours are available on project basis and on request.</i>
Finish	Semi-gloss
Density	1,41 kg/l mixed product
Volume solids	>90%
VOC quality	150 g/l
Shelf life	At least 6 months after the date of production, if stored cool in unopened packaging and protected against frost. Drums should always be placed on pallets to avoid direct contact with the floor.

## Application information

Method	Roller and brush	
Usage	0,15 – 0,25 kg/m <sup>2</sup> /layer <i>Surface, processing method and desired colour dependent. Must allow for two coats minimum.</i>	
Mixing ratio	795 gram A : 205 gram B	
Potlife	At 15 °C	approx. 35 minutes
	At 20 °C	approx. 30 minutes
	At 25 °C	approx. 25 minutes
Application temp.	Surface	-10 and +30 °C
	Product	+10 and +25 °C
Walkable	At -10 °C	After 2,5 hours
	At 0 °C	After 2 hours
	At 10 °C	After 1,5 hours
	At 20 °C	After 1 hour
	At 25 °C	After 45 minutes
Recoat time	At -10 °C	Min. 2,5 hours Max. 48 hours
	At 0 °C	Min. 2 hours Max. 48 hours
	At 10 °C	Min. 1,5 hours Max. 48 hours
	At 20 °C	Min. 1 hour Max. 24 hours
	At 25 °C	Min. 45 min Max. 24 hours
Chemical resistant*	After 3 x 24 hours	
Mechanical resistant*	After 2 – 3 hours	
Water resistant*	After 2 – 3 hours	
Dilution	Preferably none, otherwise ProFast TH-S. A maximum of 5% only to be added once base(A) and hardener(B) have been mixed. Adding thinner can affect the curing times.	
Cleaning agent	Roca Cleaner R5518 (equipment)	

The times and values given are approximate and are affected by fluctuating surface and environmental conditions such as (product)temperature, relative humidity and layer thickness. Values are given at 0,15 kg/m<sup>2</sup>/layer

## Mixing instructions

2-component products must always be mechanically mixed, preferably with a continuously adjustable mixing machine on low speed (300 – 400 RPM) or other suitable mixing equipment. Use a clean mixing rod which matches the size of the container. Mixing too fast and too long should be avoided in order to minimise air entrapment.

First mix component A and component B until it is a homogenous mixture. Pour a part of the mixture back in the harder can and mix to include all harder materials. Afterwards, pour this mixture back into the base can and mix again until it is a homogenous mixture. Transfer the mixture to a clean mixing bucket/tub.

\* At 20 °C and 65% RH surface.  
\*\* At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21  
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future

# ProFast Topcoat 703-AS

When mixing parts, both components must be mixed separately and carefully and weighed accurately.

## Notes during application

Wear the correct PPE during processing and consult the safety data sheets beforehand.

Allow the material to acclimatize for at least 24 hours. Avoid wide temperature differences between the product and the surface as this could have an adverse effect on the end-product.

2-component products may only be applied when the relative humidity is between 35 - 85%. A low humidity will result in slower curing.

The minimum surface temperature is -10 °C and the temperature of the surface to be treated and the uncured product must be 3 °C above the dew point. See the dew point table.

Low surface temperatures affect the ease of application and usage of the coating per square meter. If necessary, the product can be diluted. See application information.

The curing process occurs more quickly at higher temperatures and slower at lower temperatures. The potlife is partly dependent on the product temperature. The curing of the product depends on the applied layer thickness. From a usage of 0,25 kg/m<sup>2</sup>, the curing time increases.

After mixing, apply a thin, closed layer to the surface using a brush or fleece roller. Then roll again with a (50 or 70 cm) floor roller.

The development of puddles needs to be prevented because it will strongly influence the drying time. A layer that is too thick will (partially) destroy the anti-slip effect.

With some colours a second layer may be necessary. We recommend using ProFast Topcoat 70-C in the same colour as ProFast Topcoat 703-AS as the first underlying layer.

## Surface and circumstances

### Mineral surfaces

The surface must be absorbent in nature. The surface must be healthy, with a minimum compression strength of 25 MPa and a minimum adhesion strength of 1,5 MPa for normal used flooring and 2 MPa for heavy load flooring.

The surface must be clean and free of grease. All loose components must be removed. Concrete must be at least 28 days old. Any

cement skin must be removed. Monolithic floors must be sanded and any dust must be removed.

### Moisture content surface

- cement-bound : < 10% CM (parts by weights)
- plaster-bound : < 0,5% CM (parts by weights)

The surface should be free of any free water film and must be free from pressure or rising water from the subsoil.

- Floors
  - Apply a layer ProFast Primer RW with a usage of 0,10 – 0,15 kg/m<sup>2</sup>/layer.
  - After the primer is cured, thoroughly sand mechanically until the surface is smooth and remove all dust.
  - Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
  - Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.

### Hotspray Surfaces

Can be used as a topcoating on hotspray systems with a shore A hardness >80 approx. 5.

- Floors
  - Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
  - Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.

### Wooden surfaces

The surface must be dry, clean and free of grease.

- Apply a layer ProFast Primer RW with a usage of 0,10 – 0,15 kg/m<sup>2</sup>/layer.
- After the primer is cured, thoroughly sand mechanically until the surface is smooth and remove all dust.
- Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
- Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.

### Metal surfaces

The following applies in general. The surface must be free of substances which may have a negative effect on adhesion, such as oils and fats.

- Steel, sanded
  - Thoroughly sand mechanically until the surface is matt and remove all dust.

\* At 20 °C and 65% RH surface.  
\*\* At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21  
www.prokol.com • info@prokol.com

**Liquid synthetic materials for a sustainable future**

# ProFast Topcoat 703-AS

- Pre-treat surface with TX Adhesion Promotor
- Apply a layer ProFast Primer RW with a usage of 0,10 – 0,15 kg/m<sup>2</sup>/layer. Prevent from puddles.
- Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
- Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.
- Steel, blasted
  - Surface blasting, Sa 2,5, 75 -100 microns, DIN EN ISO 12 944. Then thoroughly remove all dust. Formation of surface rust must be avoided at all times.
  - Pre-treat surface with TX Adhesion Promotor
  - Apply a layer ProFast Primer RW with a usage of 0,10 – 0,15 kg/m<sup>2</sup>/layer..
  - Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
  - Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.
- Aluminium
  - Thoroughly sand mechanically until the surface is matt and remove all dust.
  - Pre-treat surface with TX Adhesion Promotor
  - Apply a layer ProFast Primer RW with a usage of 0,10 – 0,15 kg/m<sup>2</sup>/layer.
  - Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
  - Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.
- Stainless steel
  - Surface blasting, Sa 2,5, 75 -100 microns, DIN EN ISO 12 944. Then thoroughly remove all dust.
  - Pre-treat surface with TX Adhesion Promotor
  - Apply a layer ProFast Primer RW with a usage of 0,10 – 0,15 kg/m<sup>2</sup>/layer. Prevent from puddles.
  - Apply a layer of ProFast Topcoat 70-C with a usage of 0,10 – 0,20 kg/m<sup>2</sup>/layer.
  - Apply a layer of ProFast Topcoat 703-AS with a usage of 0,15 – 0,25 kg/m<sup>2</sup>/layer.

## Important

Projects and applications can vary greatly. Always contact your supplier if you have doubts about a certain application, choice of material or surface treatment.

All the technical information given in this technical information sheet is based on laboratory tests. Information can change, depending on the conditions.

\* At 20 °C and 65% RH surface.  
\*\* At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21  
www.prokol.com • info@prokol.com

## Legal notification

The information and, in particular, the recommendations concerning the application and final use of Prokol products is issued in good faith based on Prokol's current knowledge and experience of products that are correctly stored, handled and applied under normal conditions.

In practice, the differences in materials, surfaces and local conditions are such that no guarantee can be given concerning the marketability or suitability for a certain objective, nor can any liability arise from any legal relationship based on this information, nor from any written recommendations or other advice that is given. The property rights of third parties must be respected.

Prokol guarantees that its products are free from manufacturing faults. Multi-component products are a finished product once the components have been mixed and processed. When mixed and processed correctly, the product will achieve the specifications given. Prokol can only guarantee the product when surfaces are processed and pre-treated correctly.

All orders are accepted under the current sales and delivery conditions. Users must always refer to the most recent product safety information sheet and product information sheet for the product concerned.

Copies of the most recent editions are provided upon request and are available at [www.prokol.com](http://www.prokol.com).

The publication of this product information sheet makes all previous product information sheets for this product invalid.

**Liquid synthetic materials for a sustainable future**